

316 | 316L Stainless Steel

316 stainless plate, round and flat bar

316 316L stainless steel stockholders and suppliers, delivering throughout the UK.

316 grade e is a chromium nickel molybdenum austenitic grade which is suitable for use in severely corrosive conditions. The addition of molybdenum gives it a better corrosion resistance than other austenitic stainless steel grades such as 304. It achieves a higher resistance to pitting and crevice corrosion in a chloride environment. The 316L grade has a reduced carbon content to improve corrosion resistance after welding.

Related Specifications

1.4401 1.4404 BS EN 10088-1 X2CrNiMo17-12-2
AISI ASTM

Alternative stainless steel grades we supply

[17/4PH](#) | [FV520B](#) | [S31254](#) | [904L](#) | [310](#) | [321](#) | [304](#)
[440B](#) | [440C](#) | [420](#) | [410](#) | [416](#) | [431](#) |

Form of Supply

West Yorkshire Steel are suppliers and stockholders of round bar, plate and sheet. Sawn blanks can be provided cut to your requirements as one offs or multiple cut pieces. 316 precision ground bar can be supplied, providing a high quality precision ground bar to close tolerances. this grade is available in plate which can be supplied as plasma cut pieces and sheet which can be guillotined to size.



- Flat
- Diameter
- Plate

Contact our experienced sales team who will assist you with your 316 enquiry.

Applications

Used widely in industries such as chemical, construction, aerospace and automotive. Typical applications are exhaust manifolds, heat exchangers, bellows, oil refinery equipment, marine equipment, pulp paper and textile processing equipment.

Analysis

Carbon*	0.08% max	Silicon	1.00% max
Manganese	2.00% max	Nickel	10.00-14.00%
Chromium	16.00-18.00%	Molybdenum	2.00-3.00%
Sulphur	0.03% max	Phosphorous	0.03% max

(*Carbon content on 316L 0.03% max)

Corrosion Resistance

316 stainless steel grade is more resistant to atmospheric and other mild types of corrosion than that of other austenitic stainless steel grades, such as 303, 304, 321 and 310. As a molybdenum bearing stainless it is considerably more resistant to solutions of sulphuric acid and phosphoric acid than that of other austenitic grades. 316 has a better resistance to pitting corrosion and stress corrosion cracking in chloride solutions to that of other non molybdenum bearing stainless steel grades.

Welding

Stainless steel 316 is readily weldable with most welding procedures. Oxyacetylene welding is not recommended due to possible carbon pick up in the weld area. With its lower carbon content 316L stainless is preferred to standard 316 as it can be welded without loss of corrosion resistance due to intergranular carbide precipitation. Post weld annealing is not normally required, except for service in more extreme conditions. We recommend you contact your welding consumables supplier who should provide you full assistance and information on welding stainless steel.

Forging

Heat the 316 slowly and uniformly throughout the section to 1150-1200°C. Re heat as necessary and avoid working below 900°C. Cool in air. Forgings will require annealing in order to obtain optimum corrosion resistance.

Scaling Temperature

The oxidation resistance of a stainless steel specification is traditionally termed as the scaling temperature. This is the temperature at which the oxidation rate of a stainless steel becomes unacceptably high. The safe scaling temperature for continuous service of 316 is 875°C. In an oxidising and reducing sulphurous atmosphere the scaling temperature of 316 stainless is lowered.

Typical Mechanical Properties

Temp °C	Density Kg/m ³	Mean Coefficient of Thermal Expansion	Modulus of Elasticity kg/mm	Electrical Resistivity Ω mm ² /m	Specific Heat Capacity kcal°C
20	7.90	16.5x10 ⁻⁶	20000	0.75	0.105

Certification

Stainless steel 316 / 316L grade is available with BS EN 10204 3.1 mill certificate, please request when placing any orders.

Quality Assured Supply

316 stainless steel is supplied in accordance with our ISO 9001:2015 registration.



West Yorkshire Steel Ltd
Sandbeck Industrial Estate,
Wetherby, Leeds,
LS22 7DN UK

Call: 01937 584440
Fax: 01937 580128
Email: sales@westyorkssteel.com



QUOTE ME



Information provided on our datasheets has been drawn from various recognised sources, including British, European and International Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources. Material supplied by the Company may vary significantly from this data but will conform to all relevant and applicable standards. Any of the products detailed may be used for a large range of purposes and as WYS has no control over their use; WYS specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied. © West Yorkshire Steel Ltd. All Rights Reserved.