



60WCrV7 Tool Steel

Quality 60WCrV7 tool steel cut and delivered straight to your tool room, whatever size you need.

60WCrV7 tool steel stockholders and suppliers, delivering to the whole of the UK.

West Yorkshire Steel are stockholders and suppliers of 60WCrV7 tool steel round bar. 60WCrV7 is an alloy shock-resisting tool steel for both hot and cold work applications. The tungsten content of this tool steel grade confers fatigue resistance, the chromium content gives depth of hardness and resistance to abrasion. 60WCrV7 tool steel is suitable for cold work tools subject to heavy shock and uneven loading; for example, press tools used for punching heavy gauge material, shear blades, nut blanking tools, perforating and piercing punches. This steel is also used with great success for chisels and punches required for heavy work on hard and tough materials. 60WCrV7 tool steel is resistant to heat checking. It is suitable for hot work applications where high fatigue strength in combination with medium hot hardness is desirable. Tools made from this tool steel may be water cooled in service with little risk of cracking.

Form of Supply

West Yorkshire Steel are stockholders and suppliers of round bar. Diameters in 60WCrV7 can be sawn to your required lengths as one offs or multiple cut pieces. Ground tool steel bar can be supplied, providing a quality precision finished bar to your required tolerances. Ground tool steel bar can be supplied, providing a quality precision finish bar to close tolerances.



Contact our experienced sales team who will assist you with your enquiry.

■ Diameter

DIN Standard steel grades we supply

[45NiCrMo16](#) | [55NiCrMoV7](#) | [90MnCrV8](#)
[42CrMo4](#) | [X45NiCrMo4](#) | [60WCrV8](#) | [31CrMoV9](#)
[X100CrMoV5](#) | [X153CrMoV12](#) | [X210Cr12](#)
[60WCrV7](#) | [X210CrW12](#) | [X40Cr14](#) | [X40CrMoV5-1](#)
[40CrMnMoS8-6](#) | [HS6-5-2C](#) | [40CrMnMo7](#)
[X155CrMoV12-1](#) | [100MnCrW4](#)

Applications

Typical hot work applications for 60WCrV7 tool steel include mandrel bars for drawing steel tubes. Medium temperature applications include swaging, forming and gripper dies, also punching, piercing and trimming dies. Other applications include shear blades working at medium temperature including flying shear blades.

Typical Analysis

Carbon	0.55-0.65%	Chromium	0.90-1.20%
Manganese	0.15-0.45%	Silicon	0.50-0.70%
Tungsten	1.80-2.10%	Phosphorous	0.03% max
Vanadium	0.10-0.20%	Sulphur	0.03% max

Forging

Heat carefully to 1000-1050°C and forge with light rapid blows. Reheat when temperature falls below 900°C if further work remains to be done. After forging, cool slowly, preferably in a furnace.

Annealing

Heat the 60WCrV7 tool steel component slowly and uniformly to 800-810°C. Soak thoroughly for two to three hours and cool slowly in the furnace to room temperature.

Stress Relieving

For applications where distortion must be at a minimum or where the machining operations have been severe, we recommend stress relieving just before the tools are finish machined in order to relieve machining strains. Heat slowly to 700°C and allow to cool in the air.

Hardening

Pre heat at 650°C followed by rapid increase of temperature to the hardening temperature of 900-950°C. Quench in oil.

Tempering

Heat slowly to the required tempering temperature, soak thoroughly for two hours per 25mm section and allow to cool in still air. For hot work applications, a minimum tempering temperature of 550°C should be used.

Temperature °C	150	200	250	350	400
Hardness HRC	58-56	56-54	55-53	53-51	52-49

Heat Treatment

Heat treatment temperatures, including rate of heating, cooling and soaking times will vary due to factors such as the shape and size of each 60WCrV7 steel component. Other considerations during the heat treatment process include the type of furnace, quenching medium and work piece transfer facilities. Please consult your heat treatment provider for full guidance on heat treatment of 60WCrV7 tool steel.

Quality Assured Supply

60WCrV7 tool steel is supplied in accordance with our ISO 9001:2015 registration.



West Yorkshire Steel Ltd
Sandbeck Industrial Estate,
Wetherby, Leeds,
LS22 7DN UK

Call: 01937 584440
Fax: 01937 580128
Email: sales@westyorkssteel.com



QUOTE ME



Information provided on our datasheets has been drawn from various recognised sources, including British, European and International Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources. Material supplied by the Company may vary significantly from this data but will conform to all relevant and applicable standards. Any of the products detailed may be used for a large range of purposes and as WYS has no control over their use; WYS specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied. © West Yorkshire Steel Ltd. All Rights Reserved.