



655M13

Quality 655M13 cut and delivered in round bar..

655M13 steel stockholders and suppliers, delivering to the whole of the UK.

655M13 case hardening steel suppliers and stockholders, delivering to the whole of the UK. West Yorkshire Steel are suppliers of 655M13 in round bar. Diameters can be supplied as full lengths or cut pieces. It is a 3% nickel, chromium, molybdenum case hardening steel grade. After carburising 655M13 gives a hard case with a strong core, whilst retaining a remarkable degree of toughness. 835M15 is also available. [835M15](#) is an alternative case hardening steel grade with a slight increase in the molybdenum content which can improve mechanical properties in heat treatment.

Alternative [alloy steel](#) grades we supply

[605M36](#) | [708M40](#) | [709M40](#) | [817M40](#) | [826M40](#)
[835M30](#) | [535A99](#) | [080A15](#) | [722M24](#) | [905M39](#)

Form of Supply

West Yorkshire Steel are stockholders and suppliers of 655M13 round bar. Diameters in 655M13 can be sawn to your required lengths as one offs or multiple cut pieces. Ground steel bar can be supplied, providing a case hardening steel precision ground bar to your close tolerances.

Applications

As a carburising steel grade it is suitable for roller and ball bearings of extra light section, aeroplane and motor crankshafts requiring hard surfaces for roller paths, connecting rods with case-hardened ends, as well as highly stressed gudgeon pins, gears and certain types of collets.



Contact our experienced sales team who will assist you with your enquiry.

■ Diameter

Analysis

Carbon	0.10-0.16%	Silicon	0.10-0.35%
Manganese	0.35-0.60%	Chromium	0.70-1.00%
Nickel	3.00-3.75%	Phosphorous	0.035% max
Sulphur	0.04% max		

Carburising / Case Hardening

Case hardening will give a hard wear resisting surface and a tough core strength 655M13. Surfaces must be free from dirt and grease, and of low sulphur content. Case hardening can be carried out in salt baths with selected content depending on the type of salt and the depth of penetration required. Other considerations during the heat treatment process include the type of furnace, quenching medium and work piece transfer facilities. Time, temperatures and salt selection will be advised by your heat treatment provider.

Tensile Strength N/mm ²	Elongation %	Impact Izod J	Impact KCV J	Hardness HB	Reduction of Area %
1100	15	40	35	341	50

(* blank case hardened – 19mm test piece)

Softening

If it is necessary to soften the 655M13 for machining between the carburising and subsequent heat treatment stages, heat to 640-650°C. Soak at this temperature for 1 to 2 hours and cool slowly in the furnace or in air.

Heat Treatment

Heat treatment temperatures, including rate of heating, cooling and soaking times will vary due to factors such as the shape and size of each 655M13 steel component. Other considerations during the heat treatment process include the type of furnace, quenching medium and work piece transfer facilities. Please consult your heat treatment provider for full guidance on heat treatment of 655M13 case hardening steel.

Certification

655M13 alloy steel is available with a cast and analysis certificate or BS EN 10204 3.1 mill certificate, please request when placing any orders.

Quality Assured Supply

655M13 is supplied in accordance with our ISO 9001:2015 registration.



West Yorkshire Steel Ltd
Sandbeck Industrial Estate,
Wetherby, Leeds,
LS22 7DN UK

Call: 01937 584440
Fax: 01937 580128
Email: sales@westyorkssteel.com



QUOTE ME



Information provided on our datasheets has been drawn from various recognised sources, including British, European and International Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources. Material supplied by the Company may vary significantly from this data but will conform to all relevant and applicable standards. Any of the products detailed may be used for a large range of purposes and as WYS has no control over their use; WYS specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied. © West Yorkshire Steel Ltd. All Rights Reserved.