

EN26W

Quality EN26W cut and delivered in rounds, whatever size you need.

EN26 EN26W stockholders and suppliers, delivering to the whole of the UK.

EN26 is a 2.5% nickel chromium molybdenum high tensile grade, usually supplied hardened and tempered to W condition. EN26W has a tensile of 1075/1225 N/mm². It is suitable for applications which require higher tensile and yield strength than EN24 or EN25 specifications. EN26W round bar is available from stock. When required it can be induction or flame hardened and is also suitable for nitriding.


We welcome export enquiries for alloy steel. Contact our sales office and consult our shipping policy for further details.

Alternative [alloy steel](#) grades we supply

[EN16T](#) | [EN19T](#) | [EN24T](#) | [EN26W](#) | [EN30B](#) | [EN31](#)
[EN32](#) | [EN36](#) | [EN40B](#) | [EN41B](#) | [EN45](#) | [EN47](#)

Form of Supply

West Yorkshire Steel are stockholders and suppliers of EN26W round bar. Diameters can be sawn to your required length as one offs or multiple cut pieces. Ground alloy steel bar can be supplied, providing a high tensile engineering steel precision ground bar to tight tolerances.



Contact our experienced sales team who will assist you with your enquiry.

■ Diameter

Applications

EN26W is a commonly used engineering steel for applications that require a higher tensile than EN24T. Typical applications include gears, shafts, spindles, pins, rams, turbine discs and torsion bars.

Analysis

Carbon	0.36-0.44%	Silicon	0.10-0.35%
Manganese	0.50-0.70%	Nickel	2.30-2.80%
Chromium	0.50-0.80%	Molybdenum	0.40-0.70%
Phosphorous	0.05% max	Sulphur	0.05% max

Forging

Pre heat carefully, then raise the temperature to 1150-1200°C and hold at temperature until thoroughly soaked and suitable to forge. Do not forge below 850°C. After forging the steel should be cooled slowly.

Annealing

Heat slowly to 790-840°C. Hold until the temperature is uniform throughout the steel. Cool in a furnace.

Hardening

EN26W is supplied ready heat treated. If further heat treatment is required annealed EN26 should be heated to 820-850°C and hold until the temperature is uniform through the section. Quench the EN26 steel in oil, water or polymer as required.

Flame & Hardening

EN26 can be flame or induction hardened to obtain a good surface hardness.

Tempering

Heat the component to the required tempering temperature (450-660°C) and thoroughly soak for one hour per 25mm thickness of section, cool in still air.

Typical Mechanical Properties*

Condition	Tensile N/mm ²	Yield N/mm ²	Elongation %	Izod KCV J	Hardness Brinell
U	925-1075	755	12	42	269-331
V	1000-1150	850	12	42	293-352
W	1075-1225	940	11	35	311-375
X	1150-1300	1020	10	28	341-401
Y	1225-1375	1095	10	21	363-429
Z	1550	1235	5	9	444

(subject to ruling section*)

Heat Treatment

Heat treatment temperatures, including rate of heating, cooling and soaking times will vary due to factors such as the shape and size of each alloy steel component. Other considerations during the heat treatment process include the type of furnace, quenching medium and work piece transfer facilities. Please consult your heat treatment provider for full guidance on heat treatment of alloy steel.

Certification

EN26W alloy steel is available with a cast and analysis certificate or BS EN 10204 3.1 mill certificate, please request when placing any orders.

Quality Assured Supply

EN26W is supplied in accordance with our ISO 9001:2015 registration.



West Yorkshire Steel Ltd
Sandbeck Industrial Estate,
Wetherby, Leeds,
LS22 7DN UK

Call: 01937 584440
Fax: 01937 580128
Email: sales@westyorkssteel.com
 

QUOTE ME



Information provided on our datasheets has been drawn from various recognised sources, including British, European and International Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources. Material supplied by the Company may vary significantly from this data but will conform to all relevant and applicable standards. Any of the products detailed may be used for a large range of purposes and as WYS has no control over their use; WYS specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied. © West Yorkshire Steel Ltd. All Rights Reserved.