



## 708M40

Quality 708M40 cut and delivered in rounds or flats, whatever size you need.

**708M40 steel stockholders and suppliers, delivering to the whole of the UK.**

708M40 708M40T steel suppliers and stockholders delivering to the whole of the UK. West Yorkshire Steel are suppliers of bright drawn bar and hot rolled black bar. 708M40 is a similar grade to 709M40 but with a variation in the molybdenum content. As a high quality alloy steel specification 708M40 is usually supplied heat treated to 'T' condition. This grade offers good ductility and shock resisting properties combined with resistance to wear. With these characteristics it is a popular high tensile engineering steel with a tensile of 850°-1000N/mm<sup>2</sup>. At low temperatures it has reasonably good impact properties. It is also suitable for a variety of elevated temperature applications. For maximum wear and abrasion resistance the steel can be nitrided to give a shallow depth wear resistant case. Flame or induction hardening of 708M40T can give a case hardness of 50HRC or higher.

**Alternative [alloy steel](#) grades we supply**

[605M36](#) | [708M40](#) | [709M40](#) | [817M40](#) | [826M40](#) |  
[835M30](#) | [535A99](#) | [080A15](#) | [655M13](#) | [722M24](#) |  
[905M39](#) | [735A50](#)

### Form of Supply

West Yorkshire Steel are stockholders and suppliers of 708M40T round bar and flat section bandsaw cut. Diameters in 708M40T can be sawn to your required lengths as one offs or multiple cut pieces. 708M40T ground steel bar can be supplied, providing a high tensile steel precision ground bar to tight tolerances.



Contact our experienced sales team who will assist you with your enquiry.

- Flat
- Plate
- Diameter

## Applications

Commonly used for general engineering applications 708M40T is suitable for applications such as high tensile shafts, bolts and nuts, gears, pinions spindles and the like.

## Analysis

Carbon	0.36-0.44%	Silicon	0.10-0.35%
Manganese	0.70-1.00%	Chromium	0.90-1.20%
Molybdenum	0.15-0.25%	Phosphorous	0.035% max
Sulphur	0.05% max		

## Forging

Pre heat carefully, then raise temperature to 850-1200°C for forging. Do not forge below 850°C. After forging cool slowly in still air.

## Annealing

Heat the 708M40T slowly to 680-700°C. Cool in air.

## Hardening

This steel grade is commonly supplied ready heat treated. If further heat treatment is required annealed 708M40 should be heated slowly to 860-890°C and after adequate soaking at this temperature quench in oil. Temper as soon as tools reach room temperature.

## Tempering

Heat carefully to a suitable temperature selected by reference to a tempering chart or table. Soak at the temperature for 2 hours per 25mm of ruling section, then allow to cool in air. Tempering between 250-375°C is not advised as tempering within this range will reduce the impact value.

## Typical Mechanical Properties\*

Condition	Tensile N/mm <sup>2</sup>	Yield N/mm <sup>2</sup>	Elongation %	Izod KCV J	Hardness Brinell
S	777-925	555	13	22	223-277
T	850-1000	650	13	35	248-302
U	925-1075	755	12	42	269-331

(subject to ruling section\*)

## Heat Treatment

Heat treatment temperatures, including rate of heating, cooling and soaking times will vary due to factors such as the shape and size of each steel component. Other considerations during the heat treatment process include the type of furnace, quenching medium and work piece transfer facilities. Please consult your heat treatment provider for full guidance on heat treatment of 708M40T alloy steel.

## Certification

708M40T alloy steel is available with cast and analysis certificate or a BS EN 10204 3.1 mill certificate, please request when placing any orders.

## Quality Assured Supply

708M40T is supplied in accordance with our ISO 9001:2015 registration.



**West Yorkshire Steel Ltd**  
Sandbeck Industrial Estate,  
Wetherby, Leeds,  
LS22 7DN UK

Call: 01937 584440  
Fax: 01937 580128  
Email: [sales@westyorkssteel.com](mailto:sales@westyorkssteel.com)



QUOTE ME



Information provided on our datasheets has been drawn from various recognised sources, including British, European and International Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources. Material supplied by the Company may vary significantly from this data but will conform to all relevant and applicable standards. Any of the products detailed may be used for a large range of purposes and as WYS has no control over their use; WYS specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied. © West Yorkshire Steel Ltd. All Rights Reserved.